

## Neodym (NdFeB)

Neodymium magnets consist of compounds with neodymium and a compound compound with ferrite, boron and additives. At present, these magnets have the highest energy content. mixed accordingly, granulated and pre-sintered (calcined), finely ground again, compression molded and sintered.



Material	Remanence		Coercive field strength				Energy density		max. Temperature
	Br		normal, bHc		intrinsic, iHc		(BxH)max		
	kG	T	kOe	kA/m	kOe	kA/m	MGOe	KJ/m <sup>3</sup>	
N35	11,7-12,2	1,17-1,22	≥10,9	≥868	≥12	955	33-36	236-287	≤80
N38	12,2-12,5	1,22-1,25	≥11,3	≥899	≥12	955	36-39	287-310	≤80
N40	12,5-12,8	1,25-1,28	≥11,4	≥907	≥12	955	38-41	302-326	≤80
N42	12,8-13,2	1,28-1,32	≥11,5	≥915	≥12	955	40-43	318-342	≤80
N45	13,2-13,8	1,32-1,38	≥11,6	≥923	≥12	955	43-46	342-366	≤80
N48	13,8-14,2	1,38-1,42	≥11,6	≥923	≥12	955	46-49	366-390	≤80
N50	14,0-14,5	1,40-1,45	≥10,0	≥796	≥11	876	48-51	382-406	≤80
N52	14,3-14,8	1,43-1,48	≥10,0	≥796	≥11	876	50-53	398-422	≤65
N54	14,5-15,0	1,45-1,50	≥10,0	≥796	≥11	876	52-55	414-438	≤60
33M	11,3-11,7	1,13-1,17	≥10,5	≥836	≥14	1114	31-33	247-263	≤100
35M	11,7-12,2	1,17-1,22	≥10,9	≥868	≥14	1114	33-36	236-287	≤100
38M	12,2-12,5	1,22-1,25	≥11,3	≥899	≥14	1114	36-39	287-310	≤100
40M	12,5-12,8	1,25-1,28	≥11,6	≥923	≥14	1114	38-41	302-326	≤100
42M	12,8-13,2	1,28-1,32	≥12,0	≥955	≥14	1114	40-43	318-342	≤100
45M	13,2-13,8	1,32-1,38	≥12,5	≥995	≥14	1114	43-46	342-366	≤100
48M	13,7-14,3	1,37-1,43	≥12,9	≥1027	≥14	1114	46-49	366-390	≤100
50M	14,0-14,5	1,40-1,45	≥13,0	≥1033	≥14	1114	48-51	382-406	≤100
52M	14,3-14,8	1,43-1,48	≥13,1	≥1043	≥14	1114	50-53	398-422	≤100
35H	11,7-12,2	1,17-1,22	≥10,9	≥868	≥17	1353	33-36	236-287	≤120
38H	12,2-12,5	1,22-1,25	≥11,3	≥899	≥17	1353	36-39	287-310	≤120
40H	12,5-12,8	1,25-1,28	≥11,6	≥923	≥17	1353	38-41	302-326	≤120
42H	12,8-13,2	1,28-1,32	≥12,0	≥955	≥17	1353	40-43	318-342	≤120
45H	13,2-13,8	1,32-1,38	≥12,1	≥963	≥17	1353	43-46	342-366	≤120
48H	13,7-14,3	1,37-1,43	≥12,5	≥995	≥17	1353	46-49	366-390	≤120
50H	14,0-14,5	1,40-1,45	≥12,6	≥1003	≥17	1353	48-51	382-406	≤120
33SH	11,4-11,7	1,14-1,17	≥10,6	≥844	≥20	1592	30-33	239-263	≤150
35SH	11,7-12,2	1,17-1,22	≥11,0	≥876	≥20	1592	33-36	263-287	≤150
38SH	12,2-12,5	1,22-1,25	≥11,4	≥907	≥20	1592	36-39	287-310	≤150
40SH	12,5-12,8	1,25-1,28	≥11,8	≥939	≥20	1592	38-41	302-326	≤150
42SH	12,8-13,2	1,28-1,32	≥12,4	≥987	≥20	1592	40-43	318-342	≤150
45SH	13,2-13,8	1,32-1,38	≥12,6	≥1003	≥20	1592	43-46	342-366	≤150
48SH	13,7-14,3	1,37-1,43	≥12,7	≥1011	≥20	1592	46-49	366-390	≤150
28UH	10,4-10,8	1,04-1,08	≥9,6	≥764	≥25	1990	26-29	207-231	≤180

Your direct contact to us:  
René Mannel

Telefon: +49 2191 464514-00  
E-Mail: [rmannel@mannel-systeme.com](mailto:rmannel@mannel-systeme.com)

**MMT Mannel Magnettechnik GmbH**  
Karlstraße 20  
D-42857 Remscheid

T +49 2191 464 514-00 [info@mannel-systeme.com](mailto:info@mannel-systeme.com)  
F +49 2191 464 514-90 [www.mannel-systeme.com](http://www.mannel-systeme.com)

## Neodym (NdFeB)

Neodymium magnets consist of compounds with neodymium and a compound compound with ferrite, boron and additives. At present, these magnets have the highest energy content. mixed accordingly, granulated and pre-sintered (calcined), finely ground again, compression molded and sintered.



Material	Remanence		Coercive field strength				Energy density		max. Temperature
	Br		normal, bHc		intrinsic, iHc		(BxH)max		
	kG	T	kOe	kA/m	kOe	kA/m	MGOe	kJ/m <sup>3</sup>	
30UH	10,8 - 11,3	1,08-1,13	≥ 10,2	≥ 812	≥ 25	≥ 1990	28-31	223-247	≤ 180
33UH	11,3-11,7	1,13-1,17	≥ 10,7	≥ 852	≥ 25	≥ 1990	31-34	247-271	≤ 180
35UH	11,7-12,2	1,17-1,22	≥ 10,8	≥ 860	≥ 25	≥ 1990	33-36	236-287	≤ 180
38UH	12,2-12,5	1,22-1,25	≥ 11,0	≥ 876	≥ 25	≥ 1990	36-39	287-310	≤ 180
40UH	12,5-12,8	1,25-1,28	≥ 11,3	≥ 899	≥ 25	≥ 1990	38-41	302-326	≤ 180
42UH	12,8-13,2	1,28-1,32	≥ 12,1	≥ 963	≥ 25	≥ 1990	40-43	318-342	≤ 180
45UH	13,2-13,8	1,32-1,38	≥ 12,3	≥ 979	≥ 25	≥ 1990	43-46	342-366	≤ 180
28EH	10,4-10,8	1,04-1,08	≥ 9,8	≥ 780	≥ 30	≥ 2388	26-29	207-231	≤ 200
30EH	10,8-11,3	1,08-1,13	≥ 10,2	≥ 812	≥ 30	≥ 2388	28-31	223-247	≤ 200
33EH	11,3-11,7	1,13-1,17	≥ 10,5	≥ 836	≥ 30	≥ 2388	31-34	247-271	≤ 200
35EH	11,7-12,2	1,17-1,22	≥ 11,0	≥ 876	≥ 30	≥ 2388	33-36	236-287	≤ 200
38EH	12,2-12,5	1,22-1,25	≥ 11,3	≥ 899	≥ 30	≥ 2388	36-39	287-310	≤ 200
40EH	12,5-12,8	1,25-1,28	≥ 11,6	≥ 923	≥ 30	≥ 2388	38-41	302-326	≤ 200
42EH	12,8-13,2	1,28-1,32	≥ 11,7	≥ 931	≥ 30	≥ 2388	40-43	318-342	≤ 200
28AH	10,4-10,8	1,04-1,08	≥ 9,9	≥ 787	≥ 33	≥ 2624	26-29	207-231	≤ 230
30AH	10,8-11,3	1,08-1,13	≥ 10,3	≥ 819	≥ 33	≥ 2624	28-31	223-247	≤ 230
33AH	11,3-11,7	1,13-1,17	≥ 10,6	≥ 843	≥ 33	≥ 2624	31-34	247-271	≤ 230
35AH	11,7-12,2	1,17-1,22	≥ 11,0	≥ 876	≥ 33	≥ 2624	33-36	236-287	≤ 230
38AH	12,2-12,5	1,22-1,25	≥ 11,3	≥ 899	≥ 33	≥ 2624	36-39	287-310	≤ 230
40AH	12,5-12,8	1,25-1,28	≥ 11,6	≥ 923	≥ 33	≥ 2624	38-41	302-326	≤ 230

Your direct contact to us:  
René Mannel

Telefon: +49 2191 464514-00  
E-Mail: [rmannel@mannel-systeme.com](mailto:rmannel@mannel-systeme.com)

**MMT Mannel Magnettechnik GmbH**  
Karlstraße 20  
D-42857 Remscheid

T +49 2191 464 514-00 [info@mannel-systeme.com](mailto:info@mannel-systeme.com)  
F +49 2191 464 514-90 [www.mannel-systeme.com](http://www.mannel-systeme.com)